

天溯
Tian Su



深圳天溯计量检测股份有限公司
ShenZhen Tiansu Calibration and Testing Co.,Ltd.



中国认可
国际互认
检测
TESTING
CNAS L5138

Rep.No.:TSZ22030451-P03-R01

Page 1 / 16 Pages

检测报告 UN38.3

Name of sample:

Lithium Battery Power Bank

产品名称:

锂电池电源组

Model/型号规格:

HIP-51.2V200Ah

Client:

SHENZHEN SAKO SOLAR CO.,LTD

委托单位:

深圳市三科新能源有限公司

Classification:

Commission Test

检测类别:

委托测试

Shenzhen Tiansu Calibration and Testing Co.,Ltd

深圳天溯计量检测股份有限公司

Shenzhen Tiansu Calibration and Testing Co.,Ltd

深圳天溯计量检测股份有限公司

B/1,4, NO.2 Jinlong Road, Longgang District, Shenzhen, China

深圳市龙岗区宝龙街道锦龙大道2号1栋、4栋

Web: www.tiansu.org

E-mail: tsjc@tiansu.org

Tel: 0755-89457984

UN38.3



TS(SZ)-J3-001-001-A02

Name of samples: Lithium Battery Power Bank 样品名称: 锂电池电源组	Trade mark: - 商标: -
Commissioned by: SHENZHEN SAKO SOLAR CO.,LTD 委托单位: 深圳市三科新能源有限公司	Commissioner address: 608, Building C, Huanggangling, Industrial Area, HEXI Village, Xixiang Street, Baoan District, Shenzhen 委托单位地址: 深圳市宝安区西乡街道桃源社区航城工业区河西黄岗岭工业园 C 栋 608
Manufacturer by: GUANGDONG SAKO NEW ENERGY CO.,LTD. 制造单位: 广东三科新能源有限公司	Manufacturer address: Room 101, NO.1, 2nd Street, shujiu Park, Changping Town, Dongguan City, Guangdong Province, China 制造单位地址: 广东省东莞市常平镇漱旧园区二街 1 号 101 室
Manufacturer's Contact Information 制造商联系信息: Phone:13798478110 Email:6798455@qq.com	Manufacturer's Web Site 制造商网址: www.sakopower.com
Type/Model 型号规格: HIP-51.2V200Ah	shape: Prismatic 样品形状: 棱柱形
Appearance color: Blue 样品颜色: 蓝色	Sample size 样品尺寸:T(415mm)*W(480mm)*L(715mm)
Rated info. 额定信息: 51.2V/200Ah/10240Wh	Cell quantity 组成电芯数量: 16PCS
Quantity of sample: 30cells+8batteries 样品数量: 30 个电芯+8 个电池	Cell mode 电芯型号: 3.2V 270Ah
Limited charge voltage 充电限制电压: 58.4V	Cut-off voltage 放电截止电压: 44.8V
Standard charge current 标准充电电流: 40A	Max continuous charge current 最大持续充电电流: 100A
Standard discharge current 标准放电电流: 40A	Max continuous discharge current 最大持续放电电流: 100A
Receiving date 接样日期: 2022-04-02	Sample identification 样品标识序号: B01#~B08#,C01#~C30#
Completing date 完成日期: 2022-04-13	Test item: 8 items 测试项目: 8 项
Test conclusion: 检测结论: The Lithium Battery Power Bank submitted by SHENZHEN SAKO SOLAR CO.,LTD are tested according to Section 38.3 of The Seventh Revised Edition of the United Nations Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria (ST/SG/AC.10/11/Rev.7/Section38.3). The test results comply with the relevant requirements of the standard. 由深圳市三科新能源有限公司送检的锂电池电源组,依据联合国《关于危险货物运输的建议书,试验和标准手册》第七修订版第 38.3 节进行检测,测试结果符合标准相关要求。	

报告专用章
Date of Issue: Apr. 13, 2022
签发日期: 2022-04-13

批准
Approved by

段江涛

审核
Reviewed by

邓兴勇

主检
Tested by

李伟强

Rep. No.:TSZ22030451-P03-R01

Page 3 / 16 Pages

Description and illustration of the sample:

样品说明及描述:

Test item 测试项目	Sample No. 样品编号	State 状态	Remark 备注
T.1~T.5	B01#~B02#	at first cycle in fully charged states; 在第一个循环完全充电;	Battery 电池
	B03#~B04#	after 25 cycles ending in fully charged states; 在第二十五个循环完全充电;	
T.6	C01#~C05#	at first cycle at 50% of the design rated capacity; 在第一个循环充电 50%的额定容量;	Cell 电芯
	C06#~C10#	after 25 cycles ending in fully charged at 50% of the design rated capacity; 在第二十五个循环充电 50%的额定容量;	
T.7	B05#~B06#	at first cycle in fully charged states; 在第一个循环完全充电;	Battery 电池
	B07#~B08#	after 25 cycles ending in fully charged states; 在第二十五个循环完全充电;	
T.8	C11#~C20#	at first cycle in fully discharged states; 在第一个循环完全放电;	Cell 电芯
	C21#~C30#	after 25 cycles ending in fully discharged states; 在第二十五个循环完全放电;	

Description of the sampling procedure:

取样程序的说明:

/

Description of report revision:

报告修订的说明:

The report data is quoted from No.:TSZ22030451-P02-R01, This sample and original report No.:TSZ22030451-P02-R01 sample is the same sample, Only Trade mark and Model differ.

该报告数据引用于报告 TSZ22030451-P02-R01, 此样品和原报告 TSZ22030451-P02-R01 样品为同一样品, 仅商标和型号不同。

Remarks:

备注:

The Lithium Battery Power Bank by SHENZHEN SAKO SOLAR CO.,LTD are large batteries.

由深圳市三科新能源有限公司所送的锂电池电源组是大电池。

Photos of Battery\电池图片



Lithium Battery Power Bank

HIP-51.2V 200Ah

Type of Cell :	LiFePO4(Square steel shell)
Nominal Capacity :	200Ah(0.2C , 25℃)
Usable Capacity :	10240Wh
Max: Charge Current :	100A
Discharge Current :	100A
Max. DISCHG Current :	150A(30 sec.)
Charge Voltage :	55.2~57.6VDC
Operation Voltage Range :	44.8~58.4VDC
Operation Temperature :	-10℃ ~ +50℃

MADE IN CHINA

电池标签 Battery Label

Photos of Cell电芯图片



38.3.4	Procedure/测试步骤					—	
38.3.4.1	Test 1: Altitude simulation/测试 1：高度模拟					P	
	Test cells and batteries shall be stored at a pressure of 11.6kPa or less for at least six hour at ambient temperature (20℃±5℃) . 将电芯和电池在温度为 20℃±5℃,大气压力为不大于 11.6kPa 的环境中贮存不少于 6 个小时。						
	Requirement/标准要求: 1.Cells and batteries Mass loss limit: ≤0.1% . 样品质量损失≤0.1%。 2.Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。 3.No leakage, no venting, no disassembly, no rupture and no fire. 样品（电池）应无漏液、无排气、无解体、无破裂以及无着火现象的发生。						
	Result						
	测试结果						
Sample No. 样品编号	Before test 测试前		After Test 测试后		Mass loss 质量损失(%)	Residual OCV 剩余电压(%)	Test result 测试结果
	Mass 样品质量 (kg)	Voltage 开路电压(V)	Mass 样品质量(kg)	Voltage 开路电压(V)			
B01#	132.980	55.546	132.980	55.518	0.00	99.95	P
B02#	133.023	55.791	133.023	55.774	0.00	99.97	P
B03#	132.993	55.122	132.993	55.100	0.00	99.96	P
B04#	132.994	54.749	132.994	54.749	0.00	100.00	P
Other supplements : Test result "P" decides that the test item passes. 其他补充：测试结果“P”代表判定该测试项目通过。							

38.3.4	Procedure/测试步骤					—	
38.3.4.2	Test 2: Thermal test/测试 2: 温度测试					P	
	Test cells and batteries are to be stored for at least six hours at a test temperature equal to 72℃±2℃, followed by storage for at least six hours at a test temperature equal to -40℃ ±2℃, The maximum time interval between test temperature extremes in 30 minutes, This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20℃±5℃).						
	将电芯和电池在温度为 72℃±2℃的条件下贮存不少于 6 个小时, 然后, 在温度-40℃±2℃条件下贮存不少于 6 个小时, 两个温度间的间隔最长为 30min,重复操作上述步骤直到 10 次, 然后, 将其在环境温度为 20℃±5℃的条件下放置 24 个小时。						
	Requirement/标准要求:						
	1.Cells and batteries Mass loss limit: ≤0.1% . 样品质量损失≤0.1%.						
	2.Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。						
	3.No leakage, no venting, no disassembly, no rupture and no fire. 样品（电池）应无漏液、无排气、无解体、无破裂以及无着火现象的发生。						
	Result 测试结果						
Sample No. 样品编号	Before test 测试前		After Test 测试后		Mass loss 质量损失(%)	Residual OCV 剩余电压(%)	Test result 测试结果
	Mass 样品质量 (kg)	Voltage 开路电压(V)	Mass 样品质量(kg)	Voltage 开路电压(V)			
B01#	132.980	55.518	132.980	55.152	0.00	99.34	P
B02#	133.023	55.774	133.023	55.456	0.00	99.43	P
B03#	132.993	55.100	132.993	54.791	0.00	99.44	P
B04#	132.994	54.749	132.994	54.442	0.00	99.44	P
Other supplements : Test result "P" decides that the test item passes. 其他补充: 测试结果“P”代表判定该测试项目通过。							

38.3.4	Procedure/测试步骤					—	
38.3.4.3	Test 3: Vibration/测试 3: 振动					P	
	Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration, The vibration shall be a sinusoidal wave form with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes, This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting position of the cell. 将电芯和电池牢固地安装在振动台的台面上，然后开始振动。振动以正弦波形式，以 7Hz 增加至 200Hz，然后再减少回到 7Hz 为一个循环，一个循环持续 15 分钟的对数扫频。每个电芯和电池从三个互相垂直的方向上循环 12 次，3 个小时。						
	Requirement/标准要求： 1.Cells and batteries Mass loss limit: ≤0.1%. 样品质量损失≤0.1%. 2.Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%，此要求不适用于完全放完电的电池和电芯。 3.No leakage, no venting, no disassembly, no rupture and no fire. 样品（电池）应无漏液、无排气、无解体、无破裂以及无着火现象的发生。						
	Result 测试结果						
Sample No. 样品编号	Before test 测试前		After Test 测试后		Mass loss 质量损失(%)	Residual OCV 剩余电压(%)	Test result 测试结果
	Mass 样品质量 (kg)	Voltage 开路电压(V)	Mass 样品质量(kg)	Voltage 开路电压(V)			
B01#	132.980	55.152	132.980	55.141	0.00	99.98	P
B02#	133.023	55.456	133.023	55.445	0.00	99.98	P
B03#	132.993	54.791	132.993	54.786	0.00	99.99	P
B04#	132.994	54.442	132.994	54.442	0.00	100.00	P
Other supplements : Test result "P" decides that the test item passes. 其他补充：测试结果“P”代表判定该测试项目通过。							

[illegible]

38.3.4	Procedure/测试步骤	—													
38.3.4.5	Test 5: External short circuit/测试 5: 外部短路 The cell or battery to be tested shall be temperature stabilized so that its external case temperature reaches $57^{\circ}\text{C}\pm 4^{\circ}\text{C}$ and then the cell or battery shall be subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at $57^{\circ}\text{C}\pm 4^{\circ}\text{C}$. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to $57^{\circ}\text{C}\pm 4^{\circ}\text{C}$, the cell or battery must be observed for a further six hour for the test to be concluded. 保持试验环境温度稳定在 $57^{\circ}\text{C}\pm 4^{\circ}\text{C}$ ，以使电芯或电池样品外表温度达到 $57^{\circ}\text{C}\pm 4^{\circ}\text{C}$ ，然后，在此温度下，将其正负极用小于 0.1 欧姆的线路短接，待电芯或电池的外表温度恢复到 $57^{\circ}\text{C}\pm 4^{\circ}\text{C}$ 之后再持续 1 小时以上，对电芯或电池必须进一步观察 6 个小时才能下结论。	P													
	Requirement/标准要求: 1.Cells and batteries meet this requirement if their external temperature does not exceed 170°C ; 电芯或电池的外壳温度应不超过 170°C ; 2. No disassembly, no rupture and no fire during the test and within six hours after this test. 试验后 6 小时内无解体、无破裂、无起火。														
	Result 测试结果														
	<table> <tr> <th>Sample No. 样品编号</th><th>Max External Temp 样品表面最高温度($^{\circ}\text{C}$)</th><th>Test result 测试结果</th></tr> <tr> <td>B01#</td><td>57.2</td><td>P</td></tr> <tr> <td>B02#</td><td>58.2</td><td>P</td></tr> <tr> <td>B03#</td><td>57.8</td><td>P</td></tr> <tr> <td>B04#</td><td>58.4</td><td>P</td></tr> </table>		Sample No. 样品编号	Max External Temp 样品表面最高温度($^{\circ}\text{C}$)	Test result 测试结果	B01#	57.2	P	B02#	58.2	P	B03#	57.8	P	B04#
Sample No. 样品编号	Max External Temp 样品表面最高温度($^{\circ}\text{C}$)	Test result 测试结果													
B01#	57.2	P													
B02#	58.2	P													
B03#	57.8	P													
B04#	58.4	P													
Other supplements : Test result "P" decides that the test item passes. 其他补充：测试结果"P"代表判定该测试项目通过。															

38.3.4	Procedure/测试步骤	—
38.3.4.6	Test 6: Crush\Impact/ 测试 6: 挤压(适用) 撞击(不适用)	P
	Crush 挤压 A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. (a) The applied force reaches 13kN±0.78kN; (b) The voltage of the cell drops by at least 100 mV; (c) The cell is deformed by 50% or more of its original thickness. Once the maximum pressure has been obtained, the voltage drops by 100mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released. 电池芯或组成电池芯在两个平面间挤压。挤压在第一个接触点以约 1.5cm/s 的速度慢慢进行，直到下面三个选项之一达到为止： (a)作用力达到 13kN±0.78kN； (b)电池芯电压降至少达到 100mV； (c)电池厚度和最初比较变形至少 50%。 一旦达到最大压力，电压降超过 100 mV 或者电池芯变形超过 50%，压力应该解除。	
	Impact 撞击 (applicable to cylindrical cells not less than 18mm in diameter) The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm ± 0.1 mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg ± 0.1 kg mass is to be dropped from a height of 61cm ± 2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface. The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm ± 0.1 mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact. Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six hours after this test. (适用于直径不小于 18 毫米的圆柱形电池)将电池或元件电池样品平放在一个平面上，其纵轴平行于测试台面年，将一直径为 15.8 mm ± 0.1 mm 的 316 型不锈钢棒横放在电池中心位置。然后，将一质量为 9.1 kg ± 0.1 kg 的物体从 61cm±2.5 cm 的高度落向样品。样品在进行试验时，其外表温度应不超过 170°C。且试验结束后 6 个小时之内，样品应无解体、无起火现象发生。	
	Requirement/标准要求： 1.Cells and component cells meet this requirement if their external temperature does not exceed 170°C； 电芯的外壳温度应不超过 170°C； 2. No disassembly, no fire during the test and within six hours after this test.	

	试验后 6 小时内无解体、无起火。			
	Result 测试结果			
Sample No. 样品编号	OCV prior to test 试验前电压 (V)	Max External Temp 样品表面最高温度(℃)	Test result 测试结果	
C01#	3.246	23.5	P	
C02#	3.266	24.8	P	
C03#	3.243	24.4	P	
C04#	3.280	24.6	P	
C05#	3.274	24.0	P	
C06#	3.252	24.8	P	
C07#	3.281	24.2	P	
C08#	3.265	23.4	P	
C09#	3.269	23.2	P	
C10#	3.278	23.7	P	
Other supplements:				
Test result "P" decides that the test item passes.				
其他补充:				
测试结果“P”代表判定该测试项目通过。				

38.3.4	Procedure/测试步骤	—													
38.3.4.7	Test 7: Overcharge/测试 7: 过度充电 When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the or 22V, whichever is less. When the manufacturer's recommended charge voltage is more than 18V, the charging voltage of the test shall be 1.2 times maximum charge voltage. The charging current is 2 times of the maximum charging current recommended by the manufacturer. 如果厂家推荐的充电电压不超过 18V, 本测试的最小充电电压应该是两倍的厂家标定最大充电电压或者是 22V, 取其中较小者。如果厂家推荐的充电电压超过 18V, 充电电压应该为 1.2 倍的厂家标定最大充电电压。充电电流为厂家推荐的最大充电电流 2 倍。	P													
	Requirements/标准要求: No disassembly and no fire during the test and within seven days after the test. 试验样品在试验中和试验后 7 天内, 应无解体和无起火现象发生。														
	Result 测试结果														
	<table> <tr> <th>Sample No. 样品编号</th><th>OCV prior to test 试验前电压 (V)</th><th>Test result 测试结果</th></tr> <tr> <td>B05#</td><td>55.546</td><td>P</td></tr> <tr> <td>B06#</td><td>55.791</td><td>P</td></tr> <tr> <td>B07#</td><td>55.122</td><td>P</td></tr> <tr> <td>B08#</td><td>54.749</td><td>P</td></tr> </table>		Sample No. 样品编号	OCV prior to test 试验前电压 (V)	Test result 测试结果	B05#	55.546	P	B06#	55.791	P	B07#	55.122	P	B08#
Sample No. 样品编号	OCV prior to test 试验前电压 (V)	Test result 测试结果													
B05#	55.546	P													
B06#	55.791	P													
B07#	55.122	P													
B08#	54.749	P													
Other supplements : Test result "P" decides that the test item passes. 其他补充: 测试结果"P"代表判定该测试项目通过。															

Rep. No.:TSZ22030451-P03-R01

Page 15 / 16 Pages

38.3.4	Procedure/测试步骤				—
38.3.4.8	Test 8: Forced discharge/测试 8: 强制放电				P
	Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C power supply at an initial current equal to the maximum discharge current specified the manufacturer The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell, Each cell shall be forced discharged for a time interval(in hours) equal to its rated capacity divided by the initial test current(in ampere).				
	在 20℃±5℃的环境温度下, 将单个电芯连接在 12V 的直流电源上进行强制放电, 此直流电源提供每个电芯初始电流为制造厂指定的最大放电电流, 放电时间为额定容量除以初始电流。				
	Requirements/标准要求: No disassembly and no fire during the test and within seven days after the test. 试验样品在试验中和试验后 7 天内, 应无解体和无起火现象发生。				
	Result 测试结果				
Sample No. 样品编号	OCV prior to test 试验前电压 (V)	Test result 测试结果	Sample No. 样品编号	OCV prior to test 试验前电压 (V)	Test result 测试结果
C11#	2.915	P	C21#	2.900	P
C12#	2.899	P	C22#	2.874	P
C13#	2.858	P	C23#	2.859	P
C14#	2.865	P	C24#	2.916	P
C15#	2.868	P	C25#	2.917	P
C16#	2.946	P	C26#	2.906	P
C17#	2.916	P	C27#	2.862	P
C18#	2.903	P	C28#	2.860	P
C19#	2.940	P	C29#	2.920	P
C20#	2.876	P	C30#	2.871	P
Other supplements : Test result "P" decides that the test item passes. 其他补充: 测试结果“P”代表判定该测试项目通过。					

STATEMENTS

声 明

1. The test report is invalid without the official stamp of Tiansu.
本报告无检测单位印章无效。
2. This report shall not be copied partly without the written approval of Shenzhen Tiansu Calibration and Testing Co.,Ltd.
除非全部复制，否则无深圳天溯计量检测股份有限公司书面批准本报告不得部分复制。
3. This report is invalid without the signature of the approver, reviewer, and tester.
本报告无批准人、审核人及检测人签名无效。
4. The test report is invalid if altered.
本报告涂改无效。
5. Objections to the test report must be submitted to Tiansu within 15 days.
对检测报告若有异议，应于收到报告之日起十五天内向检测单位提出。
6. The test report is valid for the tested samples only.
本报告仅与送检样品有关。

----- 报告结束 -----